



Analysenbericht

XL2-99147

Messung Nr.: 626 Modus: Legierungen
Messdauer: 5,0s Zeit: 29.09.2017 17:08:54

Herstellernummer pghp007-body
User Login Marc Manusch

Werkstoffvorschlag: CW617N_CuZn40Pb2

Element		%	±	2σ	Min		Max
Kupfer	Cu	59,113	±	0,788	57,000		60,000
Zink	Zn	38,501	±	0,689	37,000		41,500
Blei	Pb	2,114	±	0,253	1,600		2,200
Eisen	Fe	0,269	±	0,079	0,000		0,300
Zinn	Sn	0,000	±	0,180	0,000		0,300
Nickel	Ni	0,000	±	0,084	0,000		0,100
Aluminium	Al				0,000		0,050

* Bitte hier Text angeben. *