



Analysenbericht

XL2-99147

Messung Nr.: 693 Modus: Legierungen
 Messdauer: 6,9s Zeit: 29.09.2017 17:42:17

Herstellernummer pghpwab002-body
 User Login Marc Manusch

Werkstoffvorschlag: CW617N_CuZn40Pb2

Element		%	±	2σ	Min		Max
Kupfer	Cu	57,999	±	0,680	57,000		60,000
Zink	Zn	39,275	±	0,605	37,000		41,500
Blei	Pb	2,270	±	0,225	1,600		2,200
Eisen	Fe	0,238	±	0,066	0,000		0,300
Zinn	Sn	0,127	±	0,098	0,000		0,300
Nickel	Ni	0,076	±	0,049	0,000		0,100
Aluminium	Al				0,000		0,050

* Bitte hier Text angeben. *