



Analysenbericht

XL2-99147

Messung Nr.: 575 Modus: Legierungen
Messdauer: 5,1s Zeit: 29.09.2017 16:35:12

Herstellernummer pghpbe006-body
User Login Marc Manusch

Werkstoffvorschlag: CW617N_CuZn40Pb2

Element		%	±	2σ	Min		Max
Kupfer	Cu	58,663	±	0,885	57,000		60,000
Zink	Zn	38,885	±	0,760	37,000		41,500
Blei	Pb	2,216	±	0,268	1,600		2,200
Eisen	Fe	0,234	±	0,079	0,000		0,300
Zinn	Sn	0,000	±	0,258	0,000		0,300
Nickel	Ni	0,000	±	0,080	0,000		0,100
Aluminium	Al				0,000		0,050

* Bitte hier Text angeben. *